

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing this collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.

1. REPORT DATE (DD-MM-YYYY) 2. REPORT TYPE Technical Papers 3. DATES COVERED (From - To)

4. TITLE AND SUBTITLE 5a. CONTRACT NUMBER

5b. GRANT NUMBER

5c. PROGRAM ELEMENT NUMBER

6. AUTHOR(S) Please see attached 5d. PROJECT NUMBER 2302

5e. TASK NUMBER M1G2

5f. WORK UNIT NUMBER 346120

7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) 8. PERFORMING ORGANIZATION REPORT

Air Force Research Laboratory (AFMC)

AFRL/PRS

5 Pollux Drive

Edwards AFB CA 93524-7048

9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) 10. SPONSOR/MONITOR'S ACRONYM(S)

Air Force Research Laboratory (AFMC)

AFRL/PRS

5 Pollux Drive

Edwards AFB CA 93524-7048

11. SPONSOR/MONITOR'S NUMBER(S) Please see attached

12. DISTRIBUTION / AVAILABILITY STATEMENT

Approved for public release; distribution unlimited.

13. SUPPLEMENTARY NOTES

14. ABSTRACT

20030129 113

15. SUBJECT TERMS

16. SECURITY CLASSIFICATION OF:

a. REPORT b. ABSTRACT c. THIS PAGE

Unclassified Unclassified Unclassified

17. LIMITATION OF ABSTRACT A

18. NUMBER OF PAGES

19a. NAME OF RESPONSIBLE PERSON Leilani Richardson

19b. TELEPHONE NUMBER (include area code) (661) 275-5015

MEMORANDUM FOR PRS (In-House Publication)

FROM: PROI (STINFO)

16 Mar 2001


SUBJECT: Authorization for Release of Technical Information, Control Number: **AFRL-PR-ED-VG-2001-054**
Miller, T.C., "Crack Growth Rates in a Propellant Under Various Conditions" (VuGraphs)

SEM Annual Conf. on Experimental Mechanics
(Portland, OR, 4-6 June 2001) (Deadline: 16 May 2001)

(Statement A)


PRESSURE EFFECTS AND SURFACE CRACKS IN A RUBBERY PARTICULATE COMPOSITE

04 Jun 01



T. C. Miller
Engineer

Propulsion Directorate
Air force research laboratory



Introduction

Introduction



Experimental
Procedure


Analysis of
Data

Results and
Discussion


Summary and
Conclusions

- Cracks develop during manufacturing, handling, and storage of rubbery particulate composites
- Previous tests used single edge notched tension (SENT) specimens. In this work, surface cracked specimens are compared with the previous results
- Results for ambient and pressurized test conditions are also compared





Rubbery Particulate Composite Experiences Pressurization During Service Life



Introduction


Experimental
Procedure

Analysis of
Data


Results and
Discussion

Summary and
Conclusions

- Pressure affects fracture behavior by suppressing void nucleation, growth, and coalescence
- Both initiation of growth and subsequent growth rates are affected
- Applying ambient test data can result in overly conservative predictions



Experimental Procedure



Introduction


Experimental
Procedure

Analysis of
Data


Results and
Discussion

Summary and
Conclusions

- Specimen geometries and test matrix
- Test conditions
- Equipment



Specimen Geometries and Test Matrix



Introduction


Experimental Procedure

Analysis of Data


Results and Discussion

Summary and Conclusions


- Razor blade cutting devices used to form initial cracks
- Side cutouts needed for surface cracked specimens
- For SENT specimens, thickness and initial crack size were varied



				a_0 [mm]	
Number of SENT specimens tested	B [mm]	2.54	7.62	12.70	
	5.08	3	3	3	
	12.70	3	3	3	
	38.10	3	3	3	
Number of surface cracked specimens tested				6	



Test Conditions



Introduction


Experimental
Procedure

Analysis of
Data

Results and
Discussion

Summary and
Conclusions

- Ambient temperature
- Ambient pressure and 6895 kpa pressure (nitrogen gas)
- Constant strain rate tests (0.067 mm/mm/min)



Equipment



Introduction



Experimental
Procedure

Analysis of
Data

Results and
Discussion


Summary and
Conclusions

- Testing machine
- Pressure test chamber
- Videotape equipment





Fixture Is Used to Apply Uniform Displacement Boundary Conditions




Introduction

Experimental
Procedure

Analysis of
Data


Results and
Discussion

Summary and
Conclusions





Analysis of Data



Introduction

Experimental
Procedure

Analysis of
Data

Results and
Discussion


Summary and
Conclusions

- Step 1: data acquisition
- Step 2: determining da/dt and K_1
- Step 3: relating da/dt and K_1



Analysis of Data

Step 1: Data Acquisition



Introduction


Experimental
Procedure

Analysis of
Data

Results and
Discussion

Summary and
Conclusions

- Use videotape to determine initiation of growth
- Use videotape to measure crack size vs. Time from initiation until maximum load
 - For surface cracks, depth could not be directly measured
- Use test machine data to determine loads at these same times



Analysis of Data

Step 2: Determining Da/dt and K_I

Introduction


Experimental
Procedure

Analysis of
Data

Results and
Discussion

Summary and
Conclusions

- Use load and geometric correction factors to determine K_I at these same times
 - Geometric correction factors come from finite element analyses
 - For surface cracks, semicircular crack front is assumed throughout growth
- Use crack size vs. Time data to determine da/dt at these same times
 - nonuniform*
I have a problem with "nonuniform". Would something like "irregular" or "irregular" be better?
 - Crack speed is nonuniform due to microstructural phenomena
 - Polynomial curve fits of a vs. T are used; derivatives give growth rate



Nonuniform Crack Growth

Nonuniform irregular!!!



Introduction

Experimental
Procedure

Analysis of
Data

Results and
Discussion


Summary and
Conclusions





Analysis of Data

Step 3: Relating Da/dt and K_I



Introduction

Experimental
Procedure

Analysis of
Data

Results and
Discussion


Summary and
Conclusions

- Da/dt and K_I can now be related for each test:

$$\frac{da}{dt} = CK_I^m$$



Results and Discussion



Introduction

Experimental
Procedure

Analysis of
Data


Results and
Discussion

Summary and
Conclusions

- Ambient vs. Pressurized test condition comparisons
- SENT and surface cracked specimen comparisons



Ambient Vs. Pressurized Conditions



Introduction


Experimental
Procedure


Analysis of
Data

Results and
Discussion


Summary and
Conclusions

- Pressure causes crack growth to slow
- Microstructural explanation
- Implication: ambient data may be overly conservative for pressurized service conditions





SENT and Surface Cracked Specimen Comparisons



Introduction


Experimental Procedure

Analysis of Data

Results and Discussion

Summary and Conclusions

- Similar growth rates found for both geometries
- Implication: SENT data can be used instead of testing with surface cracked specimens





Combination of All Data




Introduction

Experimental
Procedure

Analysis of
Data

Results and
Discussion

Summary and
Conclusions





Introduction


Experimental
Procedure

Analysis of
Data

Results and
Discussion

Summary and
Conclusions

What's the Q & A about?



Summary and Conclusions

- **Summary:** this work has investigated the effect of pressure on fracture behavior of a rubbery particulate composite, and has compared the results for two different crack geometries under pressure. Pressure delays the onset of crack growth and slows the subsequent growth rate. The results for the two specimen geometries tested under pressure (SENT and surface cracked specimens) show good agreement.
- **Conclusions:**
 - Pressure inhibits the start of crack growth and slows the subsequent crack growth
 - Pressurized test data should be used to test for pressurized service conditions
 - SENT specimens can be used rather than surface cracked specimens

For the material and crack geometry considered in this study,